

518,692

Patent PCT/PTO 16 DEC 2004

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date  
8 January 2004 (08.01.2004)

PCT

(10) International Publication Number  
WO 2004/003072 A1

(51) International Patent Classification<sup>7</sup>: C08L 23/10, B29C 45/00 // (C08L 23/10, 23:08)

(74) Agent: GAVERINI, Gaetano; Basell Poliolefine Italia S.p.A., Intellectual Property, Via Pergolesi, 25, I-20124 Milano (IT).

(21) International Application Number:  
PCT/EP2003/006093

(81) Designated States (national): AU, BR, CA, CN, CO, CZ, HU, ID, IL, IN, JP, KR, MX, NO, PH, PL, RO, RU, SG, SK, UA, US, YU, ZA.

(22) International Filing Date: 11 June 2003 (11.06.2003)

(84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

(25) Filing Language: English

Declarations under Rule 4.17:

(26) Publication Language: English

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
- of inventorship (Rule 4.17(iv)) for US only

(30) Priority Data:  
02014213.9 26 June 2002 (26.06.2002) EP

Published:

(71) Applicant (for all designated States except US): BASELL POLIOLEFINE ITALIA S.P.A. [IT/IT]; Via Pergolesi, 25, I-20124 Milano (IT).

— with international search report

(72) Inventors; and

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(75) Inventors/Applicants (for US only): PELLICONI, Anteo [IT/IT]; Via Volta, 22, I-45030 Santa Maria Madalena, Rovigo (IT). ANGELINI, Antonella [IT/IT]; Via Val Trebbia, 16, I-44100 Ferrara (IT). SGARZI, Paola [IT/IT]; Via Borgo dei Leoni, 83, I-44100 Ferrara (IT).

WO 2004/003072 A1

(54) Title: IMPACT-RESISTANT POLYOLEFIN COMPOSITIONS

(57) Abstract: Polyolefin compositions comprising (percent by weight): 1) 55-90% of a crystalline propylene homopolymer or copolymer containing up to 15% of ethylene and/or C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefin(s) and having values of MFR equal to or higher than 25 g/10 min; 2) 10-45% of a copolymer of ethylene with one or more C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefin(s) containing from 10 to 40% of said C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefin(s); said compositions having values of MFR equal to or higher than 20 g/10 min, a total content of ethylene of 20% or more, a total content of C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefin(s) of 4.5% or more, a ratio of the total content of ethylene to the total content of C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefin(s) of 2.3 or more, a total fraction soluble in xylene at room temperature of less than 18 wt% and an intrinsic viscosity value of the fraction soluble in xylene at room temperature of 1.7 dl/g or less.